

Pozytyw = Negatyw

t	q	W _{min}	J _{y,brutto}	J _{y,eff,min}	J _{y,eff,max}	A _{brutto}	A _{eff}	i _{brutto}	Z _{max}	W _{max}	N _{cr}	R _{Rd,A}	R _{Rd,B,60}	R _{Rd,B,200}
mm	kg/m ²	cm ³ /m	cm ⁴ /m			cm ² /m	cm		mm	cm ³ /m	kN/m	kN/m		
0.70	6.69	13.28	46.47	45.17	46.47	8.52	6.24	2.33	30.82	14.03	199.55	7.28	25.46	40.68
0.75	7.17	14.50	49.79	48.73	49.79	9.13	6.89	2.33	30.74	15.23	220.48	8.35	28.98	46.13
0.80	7.65	15.72	53.11	51.60	53.11	9.74	7.54	2.33	30.69	16.46	241.12	9.47	32.67	51.82
0.88	8.41	17.67	58.42	57.18	58.42	10.72	8.58	2.33	30.61	18.41	274.50	11.41	38.96	61.49
1.00	9.56	20.63	66.39	65.51	66.39	12.18	10.17	2.33	30.50	21.32	325.31	14.63	49.28	77.23
1.15	10.99	24.42	76.35	75.15	76.35	14.00	12.18	2.33	30.36	25.04	389.82	19.18	63.65	98.93
1.25	11.95	27.00	82.99	82.07	82.99	15.22	13.54	2.33	30.30	27.55	433.34	22.53	74.09	114.60